TECHNICAL DATA SHEET

CHRYSO®EnviroMix®300

Multi-Range Water Reducing Admixture

CHRYSO CONCRETE SOLUTIONS

DESCRIPTION

High-Performance Admixture based on CHRYSO "EnviroMix" technology, specially designed for high SCM concrete mix designs. CHRYSO "EnviroMix" 300 provides high early strengths to increase SCM content in concrete and achieve substantial savings. It provides optimized workability and placeability to achieve targeted concrete quality and performance on-site while reducing jobsite time and costs.

Meets or exceeds the requirements of ASTM C-494 Type A

ADVANTAGES

- Allows better utilization of mixes incorporating high volumes of pozzolans such as fly ash
- Allows Use of high proportions of Manufactured Sand
- Improved Finish, Placement and Pumpability
- High SCM usage contributes to the protection of our environment (Reduction of CO₂ emissions encouraged by LEED directives)

FIELDS OF APPLICATION

- All Cement Types
- Ready Mix Concrete
- Manufactured Sand
- Sands with High Fines
- High SCM Replacement

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSO "EnviroMix" 300 is 3 to 14 oz/cwt (195 to 910 ml/100 kg) of cementitious material for a Type A.
- CHRYSO"EnviroMix"300 can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



TECHNICAL DATA SHEET

Multi-Range Water Reducing Admixture

CHARACTERISTICS

Product Nature	Liquid
Color	Brown
Shelf life	12 months
CI- lons content	< 0.100
Specific gravity (25°C) in g/ml	1.165
pH (25°C)	5.00

PRECAUTIONS

- CHRYSO^{*}EnviroMix^{*}300 should be stored at or above 34°F (1°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO^{*}EnviroMix^{*}300 is compatible with most CHRYSO admixtures if added separately to the concrete mix.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

Packaging :

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Applcation" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010



CHRYSO CONCRETE SOLUTIONS

P.2/2