TECHNICAL DATA SHEET

CHRYSO CONCRETE SOLUTIONS

CHRYSO®Optima 1240

High Range Water Reducing Admixture Enhanced Slump Retention

DESCRIPTION

High-Performance Admixture based on new proprietary CHRYSO [®]Optima 1000 Technology. CHRYSO [®]Optima 1240 provides excellent water reduction along with extended pumpability and slump retention over time. CHRYSO [®]Optima 1240 allows designing high-level performance concrete to meet the most challenging jobsites' requirements. Meets or exceeds the requirements of ASTM C-494 Type A and F

ADVANTAGES

- Extended Slump Life with Minimal Effect on Set time and Early Strengths
- Increases early and ultimate compressive and flexural strengths
- Provides uniform, normal-setting characteristics
- Reduced Viscosity (Stickiness)
- Reduces Job Site Water Additions

FIELDS OF APPLICATION

- All Cement Types
- Ready Mix Concrete
- High Early Strength
- Self Consolidating Concrete (SCC)
- Extended Slump Retention

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSO "Optima 1240 is 2 to 6 oz/cwt (130 to 391 ml/100 kg) of cementitious material for a Type A and 6 to 20 oz/cwt (391 to 1304 ml/100 kg) of cementitious material for a Type F.
- CHRYSO®Optima 1240 can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010



CHRYSO CONCRETE SOLUTIONS

CHRYSO®Optima 1240

High Range Water Reducing Admixture Enhanced Slump Retention

CHARACTERISTICS

Product Nature	Liquid
Color	Amber
Shelf life	12 months
CI- lons content	< 0.100
Specific gravity (25°C) in g/ml	1.070
рН (25°С)	4.00

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging :

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

PRECAUTIONS

- CHRYSO'Optima 1240 should be stored at or above 34°F (1°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO[°]Optima 1240 is compatible with most CHRYSO admixtures if they are added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalenebased admixtures including ProPel AG, or melamine-based admixtures.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

