## TECHNICAL DATA SHEET

## CHRYSO®PoreTite 77

Water Repelling and Efflorescence Reducing Admixture

# CHRYSO CONCRETE SOLUTIONS

## **DESCRIPTION**

CHRYSO\*PoreTite\*77 is a pore-blocking Admixture based on polymeric proven technology. CHRYSO\*PoreTite\*77 provides long-lasting resistance to water penetration without significantly modifying the hardened properties of drycast or ready mix concrete.

#### **ADVANTAGES**

- Superior Primary and Secondary Efflorescence Control
- Reduced Permeability and Absorption
- Improves Concrete Chemical Resistance and Durability

## FIELDS OF APPLICATION

- All Cement Types
- Permeability and Adsorption Reduction
- Concrete Blocks
- Concrete Pipe

## METHOD OF USE

#### **Dosage**

- The recommended dosage rate for CHRYSO "PoreTite"77 is 6 to 36 oz/cwt (391 to 2340 ml/100 kg) of cementitious material.
- CHRYSO\*PoreTite\*77 should be added with the initial mixing water. It should not be added with or on the dry cement.
- The optimum dosage rate of this product can only be established after trial tests to determine the amount of absorption and efflorescence control.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



## CHRYSO CONCRETE SOLUTIONS

## CHRYSO®PoreTite 77

Water Repelling and Efflorescence Reducing Admixture

### **CHARACTERISTICS**

Product Nature	Liquid
Color	White
Shelf life	6 months
CI- lons content	< 0.100
Specific gravity (25°C) in g/ml	1.000
pH (25°C)	10.00

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

#### **Packaging:**

- 55 gallon drum (210 L)
- **264** gallon tote (1000 L)
- Bulk

## **PRECAUTIONS**

- CHRYSO\*PoreTite\*77 should be stored at or above 45 °F (7 °C). If frozen, the product is not useable and should be disposed of according to local, state, and federal regulations.
- CHRYSO\*PoreTite\*77 is compatible with most CHRYSO admixtures if added separately to the concrete mix.

## SAFETY

Prior to any use, please read carefully the Safety data Sheet.

