TECHNICAL DATA SHEET

CHRYSO®TurboCast®701

Accelerating Admixture Non-Chloride



DESCRIPTION

CHRYSO*TurboCast*701 is a RJN-based new generation accelerator for concrete, designed to provide a faster set and overall enhanced concrete strengths. CHRYSO*TurboCast*701 allows reducing jobsite time and costs.

Meets or exceeds the requirements of ASTM C-494 Type C

ADVANTAGES

- Allows for Slump Retention and High Early Strength Combination
- High Early and Ultimate Strength Performance
- Reduces Curing Time
- Facilitates Early Stripping
- Reduces Curing Costs

FIELDS OF APPLICATION

- All Cement Types
- Precast Concrete
- Ready Mix Concrete
- Concrete Patching
- Very High Early Strength Concrete
- Extended slump retention

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSO "TurboCast"701 is 8 to 90 oz/cwt (520 to 5850 ml/100 kg) of cementitious material for a Type C.
- **CHRYSO** TurboCast 701 can be added with the initial water or at the end of the batching sequence. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed and the optimal dosage sequencing.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



TECHNICAL DATA SHEET

CHRYSO®TurboCast®701

Accelerating Admixture Non-Chloride



CHARACTERISTICS

| Product Nature | Liquid |
|---------------------------------|-------------|
| Color | Clear Amber |
| Shelf life | 12 months |
| CI- lons content | < 0.100 |
| Specific gravity (25°C) in g/ml | 1.230 |
| pH (25°C) | 8.00 |

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging:

- 55 gallon drum (210 L)
- **264** gallon tote (1000 L)
- Bulk

PRECAUTIONS

- CHRYSO TurboCast 701 should be stored at or above 20°F (-7°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO TurboCast 701 is compatible with most CHRYSO admixtures if they are added separately to the concrete mix.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

