TECHNICAL DATA SHEET

CHRYSO®EnviroMix®159

Full Range Water Reducing Admixtures

CHRYSO Concrete Solutions

DESCRIPTION

High-Performance Admixture based on CHRYSO "EnviroMix" technology, specially designed for high SCM concrete mix designs. CHRYSO "EnviroMix"159 provides high early strengths to increase SCM content in concrete and achieve substantial savings. It provides optimized workability and placeability to achieve targeted concrete quality and performance on-site while reducing jobsite time and costs.

Meets or exceeds the requirements of ASTM C-494 Type A & F

Envir_OMx

FIELDS OF APPLICATION

All Cement Types

Ready Mix Concrete

Manufactured Sand

High SCM replacement

ADVANTAGES

- Allows better utilization of mixes incorporating high volumes of pozzolans such as fly ash
- Proprietary finishing aid improves workability and finishability
- Reduces cracking and shrinkage
- Improves Cementitious Material Performance (More PSI/Ib)
- High SCM usage contributes to the protection of our environment (Reduction of CO₂ emissions encouraged by LEED directives)

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSO "EnviroMix"159 is 3 to 14 oz/cwt (195 to 910 ml/100 kg) of cementitious material for a Type A and 12 to 20 oz/cwt (780 to 1304 ml/100 kg) of cementitious material for a Type F.
- CHRYSO[®]EnviroMix[®]159 can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures. Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010



CHRYSO CONCRETE SOLUTIONS

CHRYSO®EnviroMix®159

Full Range Water Reducing Admixtures

CHARACTERISTICS

Product Nature	Liquid
Color	Blue green
Shelf life	12 months
CI- lons content	< 0.100
Specific gravity (25°C) in g/ml	1.180
pH (25°C)	9.00

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging :

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

PRECAUTIONS

- CHRYSO^{*}EnviroMix^{*}159 should be stored at or above 40°F (5°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO[®]EnviroMix[®]159 is compatible with most CHRYSO admixtures if added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalenebased admixtures including ProPel AG, or melamine-based admixtures.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

