TECHNICAL DATA SHEET

CHRYSO®Quad 842

Multi-Range Water Reducing Admixture



DESCRIPTION

CHRYSO*Quad 842 is the latest generation of Water-Reducing Admixture designed to enhance the use of low-cost aggregates such as manufactured sands. CHRYSO*Quad 842 provides good workability retention to achieve targeted concrete quality and performance on-site at an optimized cost.

Meets or exceeds the requirements of ASTM C-494 Type A and F

ADVANTAGES

- Allows Use of high proportions of Manufactured Sand
- Enhanced Slump Retention
- Proprietary finishing aid improves workability and finishability
- Robust When Using Sand With a High Amount of Fines
- Excellent Air Control
- Wide Range of Water Reduction With Little Impact on Set Time
- Reduces cracking and shrinkage
- Increases early and ultimate compressive and flexural strengths

FIELDS OF APPLICATION

- All Cement Types
- Use of SCMs including Natural Pozzolan
- Ready Mix Concrete
- Manufactured Sand
- Sands with High Fines
- Extended Slump Retention

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSOQuad 842 is 2 to 10 oz/cwt (130 to 652 ml/100 kg) of cementitious material for a Type A and 6 to 20 oz/cwt (391 to 1304 ml/100 kg) of cementitious material for a Type F.
- CHRYSO Quad 842 can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



CHRYSO CONCRETE SOLUTIONS

CHRYSO®Quad 842

Multi-Range Water Reducing Admixture

CHARACTERISTICS

Product Nature	Liquid
Color	Brown
Shelf life	12 months
CI [—] lons content	< 0,100 %
Specific gravity (25°C) in g/ml	1,050 ± 0,000
pH (25°C)	4,00

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging:

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

PRECAUTIONS

- CHRYSO Quad 842 should be stored at or above 40°F (5°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation. CHRYSO *Quad 842 is compatible with most CHRYSO admixtures if they are added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalenebased admixtures including ProPel AG, or melamine-based admixtures.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

