# TECHNICAL DATA SHEET

# CHRYSO®Quad 520 EMx

Multi-Range Water Reducing Admixture



## **DESCRIPTION**

CHRYSO\*Quad 520 EMx is the latest generation of Water Reducing Admixture designed to enhance the use of low-cost aggregates such as manufactured sands. CHRYSO\*Quad 520 EMx provides good workability retention to achieve targeted concrete quality and performance on-site at an optimized cost.

Meets or exceeds the requirements of ASTM C-494 Type A and F

### **ADVANTAGES**

- Allows Use of high proportions of Manufactured Sand
- Improves Finish, Placement and Pumpability
- Improves Slump Retention

## FIELDS OF APPLICATION

- All Cement Types
- Ready Mix Concrete
- Manufactured Sand
- Sands with High Fines

## METHOD OF USE

#### **Dosage**

- The recommended dosage rate for CHRYSO \*Quad 520 EMx is 3 to 10 oz/cwt (195 to 652 ml/100 kg) of cementitious material for a Type A and 7 to 20 oz/cwt (546 to 1304 ml/100 kg) of cementitious material for a Type F.
- CHRYSO®Quad 520 EMx can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



# CHRYSO CONCRETE SOLUTIONS

# CHRYSO®Quad 520 EMx

Multi-Range Water Reducing Admixture

## **CHARACTERISTICS**

Product Nature	Liquid
Color	Brown
Shelf life	12 months
CI <sup>—</sup> lons content	< 0,100 %
Specific gravity (25°C) in g/ml	1,060 ± 0,000
pH (25°C)	4,50

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

### Packaging:

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

## **PRECAUTIONS**

- CHRYSO Quad 520 EMx should be stored at or above 34°F (1°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO Quad 520 EMx is compatible with most CHRYSO admixtures if they
  are added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalenebased admixtures including ProPel AG, or melamine-based admixtures.

### SAFETY

Prior to any use, please read carefully the Safety data Sheet.

