## CHRYSO®Premia 360 EMx

High Range Water Reducing Admixture



### **DESCRIPTION**

CHRYSO\*Premia 360 EMx is a new generation high range water reducing admixture based on modified polycarboxylates. It leverages concrete strength performance to optimize mix design. CHRYSO\*Premia 360 EMx provides extended pumpability and flowability to increase productivity and reduce production costs.

Meets or exceeds the requirements of ASTM C-494 Type A and F



### **ADVANTAGES**

- High Early Strength
- Improved Finish
- Placement and Pumpability
- Reduced Viscosity (Stickiness)
- Reduces Surface Defects and Bug holes
- High Flowing Concrete without Segregation

### FIELDS OF APPLICATION

- All Cement Types
- Precast Concrete
- Post Tensioned and Prestressed Concrete
- Self Consolidating Concrete (SCC)
- Very High Early Strength Concrete
- High SCM Replacement

### **METHOD OF USE**

### **Dosage**

- The recommended dosage rate for CHRYSO \*Premia 360 EMx is 2 to 6 oz/cwt (130 to 390 ml/100 kg) of cementitious material for a Type A and 4 to 16 oz/cwt (260 to 1045 ml/100 kg) of cementitious material for a Type F.
- CHRYSO Premia 360 EMx can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



# CHRYSO CONCRETE SOLUTIONS

# CHRYSO®Premia 360 EMx

High Range Water Reducing Admixture

### **CHARACTERISTICS**

Product Nature	Liquid
Color	Amber-Brown
Shelf life	12 months
CI <sup>—</sup> lons content	< 0,100 %
Specific gravity (25°C) in g/ml	1,070 ± 0,000
pH (25°C)	4,50

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

#### **Packaging:**

- 55 gallon drum (210 L)
- 264 gallon tote (1000 L)
- Bulk

## **PRECAUTIONS**

- CHRYSO'Premia 360 EMx should be stored at or above 40°F (5°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO Premia 360 EMx is compatible with most CHRYSO admixtures if added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalenebased admixtures including ProPel AG, or melamine-based admixtures.

### SAFETY

Prior to any use, please read carefully the Safety data Sheet.

