

ZYLA® 630

Normal Water Reducing Admixture

DESCRIPTION

ZYLA® 630 water-reducing admixture is a proprietary formulation incorporating highly purified specialty organic chemicals. ZYLA® 630 promotes more complete hydration of Portland cement and has no effect on concrete air entrainment.

The ZYLA® product line of water reducers is specially formulated to have a synergistic effect with polycarboxylate-based mid-range and high-range water reducers that improve flat-work finishability.

This product contains no intentionally added chloride and as such is essentially chloride free. It is manufactured under rigid controls that provide uniform, predictable performance. ZYLA® 630 is supplied as a light brown, low viscosity liquid, and is ready-to-use as received. One gallon weighs approximately 9.1 lbs (1.1 kg/L).

ADVANTAGES

- No impact on concrete air content
- Better control of water reduction and setting times as compared to traditional lignin-based water reducers
- Synergistic performance of polycarboxylate-based mid-range and high-range water reducers, which includes water reduction, concrete strength and air control
- In the hardened state, improves the compressive and flexural strengths at all ages of concrete versus traditional lignin-based water reducers

FIELDS OF APPLICATION

ZYLA® 630 is suitable for normal weight and light weight concrete in ready-mix, precast and prestressed applications

Method of Use

Dosage

- The addition rate range of 3 to 5 fl oz/100 lbs (195 to 325 mL/ 100 kg) of cement or cementitious is typical for most applications. However addition rates of 2 to 7 fl oz/100 lbs (130 to 455 mL/100 kg) of cement or cementitious may be used if local testing shows acceptable performance. Pretesting is required to determine the appropriate addition rate for desired performance. The optimum addition rate depends on the other concrete mixture components, job conditions, and desired performance characteristics.
- The admixture shall be delivered as a ready-to-use liquid product and shall require no mixing at the batching plant or job site.

Additional Usage Recommendations

- ZYLA® 630 is used to produce concrete mixes with lower water content (typically 3% to 10% reduction), greater plasticity and higher compressive strengths. ZYLA® 630 is suitable for normal weight and light weight concrete in ready-mix, precast and prestressed applications.
- The unique chemistry of ZYLA® 630 positively impacts the finishability of concrete by providing a creamier and more homogenous texture, with more uniform bleed rate relative to traditional lignin-based water reducers. The influence of ZYLA® 630 on the finishability of lean mixes has been particularly noticeable. Floating and troweling, by machine or hand, imparts a smooth, close tolerance surface.

Equipment

- A complete line of accurate, automatic dispensing equipment is available. ZYLA® 630 may be introduced to the mix through the water

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.

TECHNICAL DATA SHEET

ZYLA® 630

Normal Water Reducing Admixture

Chryso
Concrete
Solutions

10/28/2024

holding tank discharge line. The ZYLA® product line is formulated to be free of sediment.

Complimentary Products

- ZYLA® 630 is compatible with most admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that ZYLA® 630 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see [Technical Bulletin TB-0110, Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations](#) for further recommendations.
- Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance.

CHARACTERISTICS

Product Nature	Liquid
Color	Brown
Shelf life	9 months
Cl ⁻ ions content	< 0,100 %
Specific gravity (25°C) in g/ml	1,096
pH (25°C)	9,80

PRECAUTIONS

- ZYLA® 630 will freeze at about 28°F (-2°C), but will be completely uniform after thawing and thorough agitation.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

PACKAGING

- Bulk
- 275 gallon tote
- 55 gallon drum

ADDITIONAL CERTIFICATIONS & MARKINGS

- Concrete shall be designed in accordance with *Standard Recommended Practice for Selecting Proportions for Concrete*, ACI 211..
- The admixture shall not contain calcium chloride as a functional ingredient.
- ZYLA® 630 will not promote corrosion of reinforcing steel embedded in concrete.
- It shall be used in strict accordance with the manufacturers' recommendations.
- The admixture shall comply with ASTM Designation C494, Type A and D water-reducing admixtures.
- Certification of compliance shall be made available on request.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.