

Chryso® Adva Cast 600

High Range Water Reducing Admixture

DESCRIPTION

Chryso® Adva Cast 600 is a polycarboxylate based high-range water reducer designed for the production of conventional and self consolidating concrete. It is formulated to provide extended slump life along with excellent workability without segregation.

The product is supplied as a ready to use liquid that weighs approximately 8.9 lbs/gal (1.1 kg/L).

Meets or exceeds the requirements of ASTM C494 Type A & F, and ASTM C1017 Type I.

ADVANTAGES

- Excellent moisture and air control
- Extended slump retention up to one hour
- Enhanced concrete cohesiveness with low viscosity for rapid placement
- Superior finish on cast surfaces
- Excellent early and later age compressive strength

Method of Use

Dosage

- **Chryso® Adva Cast 600** is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates for **Chryso® Adva Cast 600** can vary from 2 to 10 fl oz/100 lbs (130 to 650 mL/100 kg) with the type of application, but will typically range from 3 to 6 fl oz/100 lbs (200 to 390 mL/100 kg) of cementitious. Should conditions require using more than the recommended addition rate, please consult your representative.
- Mix proportions, cementitious content, aggregate gradations and ambient conditions will affect **Chryso® Adva Cast 600** dosage requirements. If materials or conditions require using more than the recommended addition rates, or when developing mix designs for Self Consolidating Concrete please consult your representative for more information and assistance.

Additional Usage Recommendations

- **Chryso® Adva Cast 600** is a plant added superplasticizer that is formulated to impart improved workability to concrete over an extended period of time while still achieving high early age compressive strength. **Chryso® Adva Cast 600** can be used for the production of Self Consolidating Concrete (SCC) in precast/prestressed applications and may also be used in conventional concrete production.
- **Chryso® Adva Cast 600** may be used to produce concrete in applications with very low water/cementitious ratios, where concrete stability and improved tolerance to material variability are required, while maintaining high levels of workability over long periods of time.

Equipment

- A complete line of accurate, automatic dispensing equipment is available.

Complimentary Products

- **Chryso® Adva Cast 600** is compatible with most admixtures as long as they are added separately to the concrete mix. However, **Chryso Adva Cast** products are not recommended for use in concrete containing naphthalene based admixtures including DARACEM® 19 and DARACEM® 100 and melamine based admixtures including DARACEM® 65. In general, it is recommended that **Chryso Adva Cast 600**

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.

TECHNICAL DATA SHEET



Chryso
Concrete
Solutions

09/25/2025

Chryso® Adva Cast 600

High Range Water Reducing Admixture

be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see [Technical Bulletin TB-0110](#), *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

- Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air entraining agent (such as DARAVAIR®, DAREX®, or AIRALON® 3000 product lines) is recommended to provide suitable air void parameters for freeze thaw resistance.

CHARACTERISTICS

Product Nature	Liquid
Color	Light yellow
Shelf life	12 months
Cl ⁻ Ions content	< 0,100 %
Specific gravity (25°C)	1,075
pH (25°C)	5,30

Does not contain intentionally added chloride

PRECAUTIONS

- **Chryso Adva Cast 600** will freeze at approximately 32°F (0°C) but will return to full functionality after thawing and thorough mechanical agitation.

SAFETY

Prior to any use, please read carefully the Safety Data Sheet.

PACKAGING

- Bulk
- 1000L Tote (275 gallons)
- 210 L (55 Gallons) Drum

ADDITIONAL CERTIFICATIONS & MARKINGS

- ASTM C494 Type A and F
- ASTM C1017 Type I

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.